

Dow Corning Rubber - Mold Making Industrial Application

Products available in Asia

Product (Click on link to access Product Safety Datasheet)	Description
Silastic® Thixo Additive	This clear liquid can be used with Silastic® 3481, 3483, 3487, 3498, P-1, S, S-2, T-2, T-4, V Silicone Rubbers to produce skin molds on vertical surfaces or from immovable objects.
Dow Corning® 1-2287 Cure Retardant	This product can be used to slow down room temperature cure of all addition cure (platinum cure) mold making rubbers.
Dow Corning® 732 RTV Multi Purpose Sealant, Clear	This one-part adhesive cures at room temperature and can be used to repair torn molds.
200® Fluid, 50 cst	This product can be used as a thinner to lower mixed viscosity. It can also be used as a release agent.
Dow Corning® Q3-6559 Cure Accelerator	This cure accelerator can be used to speed room temperature cure of all addition-cure (platinum cure) Mold Making silicone rubbers. It can also be used as a surface treatment to prevent inhibition.

Product (Click on link to access Product Safety Datasheet)	Description
Silastic® Thixo Additive	This clear liquid can be used with Silastic® 3481, 3483, 3487, 3498, P-1, S, S-2, T-2, T-4, V Silicone Rubbers to produce skin molds on vertical surfaces or from immovable objects.
Dow Corning® 1-2287 Cure Retardant	This product can be used to slow down room temperature cure of all addition cure (platinum cure) mold making rubbers.
200® Fluid, 50 cst	This product can be used as a thinner to lower mixed viscosity. It can also be used as a release agent.
Syl-Off® 4000 Catalyst	This cure accelerator can be used to speed room temperature cure of all addition-cure (platinum cure) Mold Making silicone rubbers. It can also be used as a surface treatment to prevent inhibition.

Products available in North America

Product (Click on link to access Product Safety Datasheet)	Description
Dow Corning® 1-2287 Cure Retardant	This product can be used to slow down room temperature cure of all addition cure (platinum cure) mold making rubbers.
Dow Corning® 732 RTV Multi Purpose Sealant, Clear	This one-part adhesive cures at room temperature and can be used to repair torn molds.
200® Fluid, 50 cst	This product can be used as a thinner to lower mixed viscosity. It can also be used as a release agent.
	This cure accelerator can be used to speed room

Dow Corning® Q3-6559 Cure Accelerator	temperature cure of all addition-cure (platinum cure) Mold Making silicone rubbers. It can also be used as a surface treatment to prevent inhibition.
Dow Corning® 236 Dispersion	This white, one-part coating can be used to prevent casting resins from sticking to wooden molding boxes and frames.
Dow Corning® HS Extender	This product can be used to extend the working time of condensation cure (tin-cure) mold making rubbers in conditions of high temperature and humidity.
Dow Corning® HS II Thixo Additive	This clear liquid can be used with Dow Corning® HS II, HS III and HS IV RTV High Strength Mold Making Silicone Rubbers and with Silastic® 3498, E, P-1, S, S-2, T-2, T-4, V Silicone Rubbers to produce skin molds on vertical surfaces or from immovable objects.
Dow Corning® HS Sprayable Catalyst (colored and clear)	These catalysts can be used with Dow Corning® HS II (colored) and HS III (clear) Bases. Primary uses include robotic skins and tooling.

Products available in South America

Product (Click on link to access Product Safety Datasheet)	Description
Dow Corning® 732 RTV Multi Purpose Sealant, Clear	This one-part adhesive cures at room temperature and can be used to repair torn molds.
200® Fluid, 50 cst	This product can be used as a thinner to lower mixed viscosity. It can also be used as a release agent.

