



## Bi-Direction 810 9/m2

Textile Structure 7005088

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

<u>Layer</u>	<u>Construction</u>	<u>Areal weight</u>	<u>Tolerance</u>	<u>Material</u>
2	0 °402	g/m <sup>2</sup>	+/- 5 %	E-glass 1.200 TEX
1	90 °402	g/m <sup>2</sup>	+/- 5 %	E-glass 600 TEX
Stitching			6 g/m <sup>2</sup>	PES [Polyester] 76 dtex
Fiber input can be determined individually				

### FURTHER CHARACTERISTICS

<u>Gauge</u>	5,0	<u>Stitching pattern</u>	tricot-warp	<u>Width (nominal)</u>	1.260 mm
<u>Stitch length</u>	3,50 mm	<u>Total tolerance</u>	5,1 %	<u>Total areal weight</u>	810 g/m <sup>2</sup>
Labelling (Standard)	Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.				
Packaging (Standard)	Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.				
Storage recommendation	With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.				

REINFORCING YOUR IDEAS