



## TECHNICAL DATASHEET

Artical Description - Y-E-1173 g/m2-1270 mm

Textile Structure 7001686 TRIAX - 1173 9/m2

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	0 °	567 g/m <sup>2</sup>	+/- 5 %	E-glass 2.400 TEX
2	45 °	300 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
1	-45 °	300 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
Stitching		6 g/m <sup>2</sup>	+/- 1 g/m <sup>2</sup>	PES [Polyester] 76 dtex

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	5	Stitching pattern	tricot-warp	Width (nominal)	1.270 mm
Stitch length	2,40 mm	Total tolerance	5,1 %	Total areal weight	1173 g/m <sup>2</sup>
Tracer yarn <sup>1</sup> 2 PC red & tracer yarn 2 PC blue					

<sup>1</sup>Position can be determined individually

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage recommendation** With original packaging: Temperature 15-35 °C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.